



湖北金龙新材料股份有限公司
HUBEI JINLONG NEW MATERIALS CO.,LTD

Test Report

SPGL:610g

颜色 (color) : 6008 蓝

日期 (date) :20201220

性能 Properties	测试方法 Test method	单位 Unit	结果 Result	
基布材质 Basic fabric Material	-	-	聚酯纤维 Polyester	
基布类型 Type of Basic fabric	-	-	1010（20*20）	
涂层类型 Type of coating	-	-	E-pvc	
Whether goods are Woven knitted/Non woven/others			Woven Fabric	
Whether filament staple yarn	warp		Filament yarn	
	weft		Filament yarn	
% filament staple yarn	Filament yarn		100	
Whethet bleached/unbled/yarns of different colours			Unbleached yarn	
Whether Texturised/Non Texturised yarn	one directio		Non Texturised yarn	
	other direction		Non Texturised yarn	
% Texturised/Non Texturised yarn	Non Texturised yarn		100	
Whether upholstery/Non upholstery	It is not possible to ascertain the specific application of the sample as the textile product may have multiple usage depending upon the user			
厚度 Thickness	DIN 53353	mm	0.50	
重量 Weight	DIN 53352	g/ m ²	619	
拉力强度 Tensile strength	DIN 53354	N/5cm	经 2606	纬 2463
撕裂强度 Tear strength	DIN 53363	N	经 337	纬 305
剥离强度 Adhesion	DIN 53357	N/5cm	121	
使用温度 Operating temp	-20 ~ 70 °C (-4~160°F)			
备注 Remark	误差正负 10%， 试验均值 Warp/Fill Tolerance +/-10%, The value is average in the lab			

检验: 尚利菊

审核: 钱珍珠



中国·湖北·随州市迎宾大道南端 2 号金龙工业园 Tel: 0722 3250315

HUBEIJINLONGGROUP